

September 2024

DISPARLON® 6150

(Thixotropic agent)

DISPARLON® 6150 is a powder type thixotropic agent composed of amide wax. DISPARLON® 6150 can be activated in sealants/adhesives at relatively low temperatures and provides excellent sag/slump resistance. Sealants and adhesives containing DISPARLON® 6150 have viscosity-stability during storage.

ADVANTAGES

- Excellent sag/slump resistance
- High shear thinning
- Excellent workability/extrudability
- Suitable for Cold-process production

APPLICATIONS

DISPARLON® 6150 is especially recommended for sealants such as modified silicone and urethane, and epoxy adhesive systems.

INCORPORATION

- Additive levels : 0.5 – 5.0 wt% on total formulation.
The optimal additive level should be determined under an actual use condition.
- Method : Standard dispersing temperature is 45 – 70 deg.C.
Addition with a kneader, planetary mixer, or twin-screw extruder is recommended.
The optimal dispersing temperature, time, and shear should be determined under an actual use condition.
After the dispersing process, do not apply shear during cooling.

TYPICAL PROPERTIES

(The following figures are typical properties, not to be used for specification.)

Appearance	White to light yellow fine powder
Melting point	124 deg.C.
Acid value	Max. 6.0
Amine	Max. 6.0
Particle size	Max. 15 µm
Apparent density	0.16



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN
(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2017 – 2024 All Rights Reserved By Kusumoto Chemicals, Ltd.