

Additives for coatings and printing inks
DISPARLON®

August 2024

DISPARLON® 6600
(Thixotropic agent for solvent-borne systems)

DISPARLON® 6600 is a powder type thixotropic agent composed of amide wax. DISPARLON® 6600 is activated in coating systems, provides thickening, anti-sagging, and anti-settling effects, and offers good workability.

ADVANTAGES

- Excellent thickening, anti-sagging, and anti-settling effects
- Effective in a wide range of activation conditions
- Good workability
- Excellent recoatability
- Powder type, 100% active matter

APPLICATIONS

DISPARLON® 6600 is recommended for general synthetic resin coatings and is especially suitable for solvent-borne epoxy/acrylic resin coatings such as marine coatings and heavy-duty anti-corrosion coatings.

INCORPORATION

- Additive levels : 0.5 – 3.0 wt% on total formulation.
The optimal additive level should be determined under an actual use condition.
- Method : Standard dispersing temperature is 50 – 70 deg.C.
Addition with a sand mil and high-speed dissolver is recommended.
The optimal dispersing temperature, time, and shear should be determined under an actual use condition.
Adding 1 – 2 % of alcohol can lower the optimum dispersion temperature.
After the dispersing process, do not apply shear during cooling.

TYPICAL PROPERTIES

(The following figures are typical properties, not to be used for specification.)

Appearance	White to light yellow fine powder
Particle size	Max. 20 µm
Bulk density	0.19
Melting point	122 deg.C.
Acid value	Max. 8.0
Amine value	Max. 8.0



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2006 – 2024 All Rights Reserved By Kusumoto Chemicals, Ltd.