

October 2024

DISPARLON[®]230

(Leveling/defoaming agent for solvent-borne systems)

DISPARLON® 230 is a leveling/defoaming agent composed of an acrylic copolymer, and is suitable for ambientcure/baking systems. **DISPARLON® 230** provides excellent leveling effect, prevents cratering and pinholes, and improves DOI. **DISPARLON® 230** may have a defoaming effect in high-polar coating systems.

ADVANTAGES

- Improves leveling and DOI
- Prevents cratering and pinholes
- Defoaming effect
- Excellent recoatability
- Silicone-free

APPLICATIONS

DISPARLON® 230 is recommended for general synthetic resin coatings and is especially suitable for mediumpolar coating systems such as unsaturated polyester coatings, alkyd/melamine coatings, and acrylic/melamine.

INCORPORATION

Additive levels: 0.2 - 1.0 wt% on total formulation.
The optimal additive level should be determined under an actual use condition.Method: Can be added at each production stage.
Post-addition at a final production stage is recommended.

TYPICAL PROPERTIES

(The following figures are typical properties, not to be used for specification.)

| (The following lighted are typical properties, not to be used for specification) | |
|--|------------------------------|
| Appearance | Clear to light yellow liquid |
| Non-volatile matter | 40 % |
| Density (20 deg.C) | 0.91 g/cm ³ |
| Viscosity (20 deg.C) | 60 mPa·s |
| Solvent | Xylene |

Kusumoto Chemicals, Ltd. -13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN (TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use. © 1997 – 2024 All Rights Reserved By Kusumoto Chemicals, Ltd.